



## NT-C rolls

Composition: 50% Viscose and 50% Polyester

Properties		Typical Value	Test Method
Weight	g/m <sup>2</sup>	78	TM 1150
Tensile Strength MD	N/12plies	450	TM 1005
Tensile Strength CD	N/12plies	300	TM 1009
Thickness	mm/4plies	3.1	TM 1031
Sinktime	S	<2	TM 1015
Absorbtion capacity	%	850	TM 1016

Note: all mentioned values are typical and should therefore only be used as guide line