

NT-W apertured, various styles

Composition 100% viscose or viscose/polyester

Properties	Typical value		Test
Weight	50	g/m <sup>2</sup>	TM 1150
Tensile strength			
MD	530	N/12plies	TM 1005
CD	92	N/12plies	TM 1009
CD wet	68	N/12plies	TM 1010
Thickness	2	mm/4plies	TM 1031
Sinktime	<2	s	TM 1015
Absorption capacity	1100	%	TM 1016

Properties	Typical value		Test
Weight	50	g/m <sup>2</sup>	TM 1150
Tensile strength			
MD	550N	12 plies	TM 1005
CD	80N	12 plies	TM 1009
CD wet	40N	12 plies	TM 1010
Thickness	1,30 mm	4 plies	TM 1031
Sinktime	< 2	s	TM 1015
Absorbtion capacity	850	%	TM 1016

Properties	Typical value		Test
Weight	80	g/m <sup>2</sup>	TM 1150
Tensile strength			
MD	500N	12 plies	TM 1005
CD	420N	12 plies	TM 1009
CD wet	270N	12 plies	TM 1010
Thickness	2,84 mm	4 plies	TM 1031
Sinktime	< 2	s	TM 1015
Absorbtion capacity	900	%	TM 1016

**Note: all mentioned values are typical and should therefore only be used as guide line**