

## ZORBEX III

White very soft spunlace nonwoven, approx. 50-55 gsm

**Composition:** 20% viscose/80% Polyester

|                            |                         | Typical Value | Tolerance | Test Method |
|----------------------------|-------------------------|---------------|-----------|-------------|
| <b>Basis Weight</b>        | <b>g/m<sup>2</sup></b>  | 55            | 50-60     | MP/09GNT/39 |
| <b>Thickness</b>           | <b>mm</b>               | 0.65          | 0.6-0.7   | MP/09GNT/38 |
| <b>Density</b>             | <b>g/dm<sup>3</sup></b> | 84            |           | MP/09GNT/12 |
| <b>Tensile Strength MD</b> | <b>N</b>                | 80            | min. 50   | MP/09GNT/01 |
| <b>Tensile Strength CD</b> | <b>N</b>                | 14            | min. 12.5 | MP/09GNT/01 |
| <b>Elongation MD</b>       | <b>%</b>                | 23            | 15-35     | MP/09GNT/01 |
| <b>Elongation CD</b>       | <b>%</b>                | 128           | 108-148   | MP/09GNT/01 |
| <b>Tear resistance MD</b>  | <b>N</b>                | 7             | min. 4.5  | MP/09GNT/29 |
| <b>Tear resistance CD</b>  | <b>N</b>                | 27            | min. 18   | MP/09GNT/29 |
| <b>Absorbtion capacity</b> | <b>%</b>                | 900           | min. 900  | MP/09GNT/44 |

**Note: all mentioned values are typical and should therefore only be used as guide line**