

ZORBEX I

(approx. 65 gsm)

Raw material: 50% Pulp / 50% Polyester

		Typical value	Test method
Basis weight	g/m ²		
Thickness	mm	0,47	ERT 30.4-89
Tensile strength MD	N/5cm	180	ERT 20.2-89 ¹
Tensile strength CD	N/5cm	35	ERT 20.2-89 ¹
Elongation MD	%	20	ERT 20.2-89 ¹
Elongation CD	%	125	ERT 20.2-89 ¹
Absorbing capacity	%	550	EN 1644-1
Absorbing time	s	< 2,0	EN 1644-1

Note: All mentioned values are typical values and should therefore only be used as a guide line.